



(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
22.11.2006 Bulletin 2006/47

(21) Application number: **99929877.1**

(22) Date of filing: **16.07.1999**

(51) Int Cl.:
B22D 11/111 (2006.01)

(86) International application number:
PCT/JP1999/003853

(87) International publication number:
WO 2000/005012 (03.02.2000 Gazette 2000/05)

(54) **MOLDING POWDER FOR CONTINUOUS CASTING OF THIN SLABS AND CONTINUOUS CASTING METHOD**

GIESSPULVER ZUM STRANGGIESSEN VON DÜNNBRAMMEN UND STRANGGIESSEVERFAHREN

POUDRE DE COUVERTURE POUR LA COULEE EN CONTINU DE BRAMES MINCES ET PROCEDE DE COULEE EN CONTINU

(84) Designated Contracting States:
AT DE GB IT

(30) Priority: **21.07.1998 JP 20512198**

(43) Date of publication of application:
16.08.2000 Bulletin 2000/33

(73) Proprietor: **SHINAGAWA REFRACTORIES CO., LTD.**
Tokyo 102-0073 (JP)

(72) Inventors:
• **MORITA, Akihiro**
Oku-gun,
Okayama 701-4265 (JP)

• **OMOTO, Tomoaki**
Akaiwa-gun,
Okayama 709-0802 (JP)

(74) Representative: **HOFFMANN EITLE**
Patent- und Rechtsanwälte
Arabellastrasse 4
81925 München (DE)

(56) References cited:
EP-A- 0 513 357 DE-A- 3 835 492
JP-A- 2 025 254 JP-A- 2 165 853
JP-A- 3 008 544 JP-A- 10 258 343

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

DescriptionTechnical Field of the Invention

5 **[0001]** The present invention relates to a mold powder for continuous casting of thin slabs having a slab thickness of 150 mm or less.

Related Art

10 **[0002]** Mold powders for continuous casting of steel generally have Portland cement, synthetic calcium silicate, wollastonite, phosphorus-containing slag, etc., as their principal raw materials, and where required, silica materials may be added, soda ash, fluorite, fluorine compounds, and alkali metal and alkaline earth metal compounds may be added as fusion regulating agents, and carbon powder may be added as a melting speed regulating agent.

15 **[0003]** Mold powder is added at the surface of the molten steel inside the mold, and performs various functions as it is consumed. Major functions of mold powder include: (1) lubricating the mold and the solidified shell; (2) dissolving and absorbing inclusions; (3) insulation of the molten steel; and (4) controlling the speed of heat transfer. For (1) and (2), it is important to regulate the softening point and viscosity of the mold powder, and it is necessary to adjust the chemical composition of the mold powder accordingly. For (3), powder properties such as melting temperature, bulk specific density, and powder spreading, which can be regulated mainly by carbon powder, are considered to be important. For 20 (4), it is important to regulate the crystallization temperature, etc., and it is necessary to adjust the chemical composition accordingly.

[0004] Worldwide technical progress in continuous casting of steel has been remarkable, and development continues. Moreover, Hot Charge Rolling (HC) and Hot Direct Rolling (HD) ratios have been improved and high-speed casting has been actively adopted to conserve energy, demands on mold powders have become stricter, and mold powders have 25 become more diverse.

[0005] Thin-slab continuous casting has been developed from conventional continuous slab casting and applied with the objective of lower cost production with less heat transfer. There are still few such casters operating in Japan, but there are many operating widely mainly in the United States, but Europe, etc., as well, numbering several tens of units, and large numbers are being constructed in a large number of other countries.

30 **[0006]** There are several types of production processes in thin-slab continuous casting, including: (1) compact-strip-production (CSP) by SMS Schloemann-Siemag; (2) in-line-strip-production (ISP) by Mannesmann Demag; (3) Tippins Samsung process (TSP) by Tippins-Samsung; (4) flexible thin-slab rolling by Danieli; (5) continuous thin slab and rolling technique by Voest-Alpine Industrieanlagenbau (VAI); and (6) medium slabs (called medium but belonging to thin slabs from 100 mm) by Sumitomo Heavy Industries.

35 **[0007]** The main characteristic of the thin-slab continuous casting processes is that cast strips are directly hot rolled immediately, and even coiled. Consequently, finished and semi-finished products can be obtained in a matter of minutes from casting to coiling. In the case of conventional continuous casting of a generic slab, the process involves transferring the cast slab strip to a heating furnace and hot rolling it through a roughing-down mill, but in the case of thin-slab continuous casting, the process has a direct connection to the heating furnace and immediate rolling without roughing 40 down in order to minimize the load on the rolling process. For that reason, thin-slab continuous casting is very-high-speed casting in which the casting speed is 3 or more meters per minute and the mold thickness is reduced.

[0008] Conventionally, Portland cement, phosphorus-containing slag, synthetic slag, wollastonite, dicalcium silicate, etc., are used as the principal raw materials for mold powders used in thin-slab continuous casting, carbonates such as Na_2CO_3 , Li_2CO_3 , MgCO_3 , CaCO_3 , SrCO_3 , MnCO_3 , and BaCO_3 , as well as NaF , Na_3AlF_6 , fluorite, MgF_2 , LiF , borax, 45 and spodumene, are used as fusion regulating agents, and carbonaceous raw materials are generally added as melting speed regulating agents.

[0009] On the other hand, mold powders employing synthetic calcium silicate as their principal raw material (semi-premelted types), and completely molten mold powders (premelted types) in which mold powder without carbon powder is first fused and pulverized to a suitable grain size, and then carbon powder is added, are also used as in the case of 50 conventional generic slab casters.

[0010] JP 020 25 254 A discloses a molten metal surface protecting material for slab casting which contains CaO , SiO_2 and Al_2O_3 as essential components, the weight ratio of CaO to SiO_2 being in the range of 0.5 to 1.6, and which contains about one kind of oxide, carbide and fluoride of alkali metals, alkaline earth metals and other metals, and additionally a carbon component as a melting rate adjusting agent. The mold powder has a surface tension of about 55 290 dyne/cm and a break point of $\leq 1000^\circ\text{C}$ and a viscosity η (poise) at 1300°C satisfying the relation with the casting speed V (m/min) of $6.0 < \eta \cdot V$. An exothermic-type mold additive for continuous casting is described in EP 0 513 357 A1. This mold additive comprises 20 to 90 wt. % of basic raw materials, 0 to 10 wt. % siliceous raw materials containing more than 50 wt. % SiO_2 , 0 to 20 wt. % flux raw materials, 2 to 30 wt. % of more than one kind of components selected

from a group comprising carbonates, bicarbonates and nitrates of alkaline metals as exothermic materials, and 3 to 30 wt. % of more than one kind of components selected from a group comprising carbon, silicon and silicon alloys as reducing materials.

[0011] JP-A-7204810 describes a mold lubricant that has a CaO/SiO₂ ratio of 0.8 to 1.3 and that contains 2 to 20 wt.-% of Al₂O₃; ≤ 4 wt.-% of Na₂O; ≤ 4 wt.-% of Li₂O, wherein (Li₂O + Na₂O) is ≤ 4 wt.-%; < 5 wt.-% of Aluminium fluoride containing F; and 0.2 to 6.0 wt.-% of carbon powder as a melting rate regulator. A continuous casting method is characterized in that the mold lubricant, which has a physical property of a crystallization rate of ≤ 10 % after cooling the mold lubricant having been melted at 1400°C and a coagulation temperature of ≥ 1070°C, is used and the relation between CaO/SiO₂ (B), Viscosity (η) at 1300°C and the casting rate V is specified.

[0012] Japanese Patent Laid-Open No. HEI 2-165853 discloses a high-speed continuous casting method for steel characterized in that its main components are CaO, SiO₂, and Al₂O₃, the ratio of CaO to SiO₂ (by weight percentage) is within a range of 0.5 to 0.95, it contains one or two or more species of oxides, carbonates, or fluorides of alkali metals, alkaline earth metals, or other metals, also contains carbon powder as a melting speed regulating agent, uses a mold powder whose surface tension at 1250°C is 290 dyne/cm or more, whose solidifying temperature is 1000°C or less, and in which a relationship between the viscosity η (poise) at 1300°C and the casting speed V (m/min) satisfies a range represented by the expression:

$$3.5 \leq \eta V \leq 6.0,$$

and the caster operates at a casting speed $V \geq 1.2$ m/min for a cast strip having a width of 600 mm or more. However, according to the preferred embodiments of the laid-open patent application in question, the casting speed is approximately 1.2 to 2.0 m/min, and it is clear this is not intended to be a very-high-speed continuous casting method with a casting speed of 3.0 m/min or more. Moreover, since the viscosity of conventional mold powders is too low for very-high-speed casting in which the casting speed is 3.0 m/min or more, heat transfer from the molten steel and the flow of fused powder between the solidified shell and the mold is not uniform, preventing achievement of stable quality and also preventing the achievement of stable operations. Therefore, the casting method described in the laid-open patent application in question and the very-high-speed continuous casting method of the present invention in which the casting speed would be 3.0 m/min or more are completely different casting methods.

[0013] At present, ordinary carbon steels such as ultra-low-carbon steels (carbon content: 100 ppm or less), low-carbon steels (carbon content: 0.02 to 0.07 wt%), medium-carbon steels (carbon content: 0.08 to 0.18 wt%), or high-carbon steels (carbon content: 0.18 wt% or more), and special steels such as stainless steel are being cast by thin-slab continuous casting. The characteristics of thin-slab continuous casting are that it is very-high-speed casting having a casting speed of approximately 3 to 8 m/min, and the mold thickness is reduced, as explained above. In addition, the molds in the casters of SMS, etc., have a special shape. That is because a submerged entry nozzle cannot be inserted since the mold thickness is very thin. For that reason, a portion called a "funnel" into which the submerged entry nozzle is inserted is widened and consequently the mold width is not straight but expands in the middle. For that reason, heat stress arises in the expanded funnel portion of the mold, and in addition, heat transfer is not uniform. Consequently, in the case of thin-slab continuous casting, a major problem has been that heat transfer is not uniform due to very-high-speed casting and surface crack occurs even in steel types such as ultra-low-carbon steel, low-carbon steel, or high-carbon steel in which the occurrence of surface crack is uncommon in conventional continuous slab casting. In the case of thin-slab continuous casting methods by other companies as well, heat transfer is not uniform due to very-high-speed casting and surface crack has similarly been a problem.

[0014] Furthermore, because it is very-high-speed casting, the molten surface level within the mold is unstable and varies greatly, and for that reason a problem has been that the powder slag gets into the molten steel at the meniscus, causing extreme deterioration in steel sheet quality.

[0015] In conventional continuous slab casting, methods which create a uniform solid shell by reducing heat transfer within the mold are effective in solving the surface crack mentioned above, and this is done by increasing the weight ratio of CaO to SiO₂ in the mold powder to raise its crystallization temperature. However, in very-high-speed casting exceeding 3 m/min, since raising the weight ratio of CaO to SiO₂ tends to increase friction between the mold and the solidified shell and lubrication by the mold powder deteriorates markedly, breakouts are more likely to occur instead, and so this measure cannot solve the above problem.

[0016] In other words, in thin-slab continuous casting, a mold powder has not yet been provided which reduces the likelihood of powder slag being entrapped in the mold without giving rise to surface crack, or which enables stable casting.

[0017] On the other hand, medium-carbon steels having a carbon content in a peritectic range of 0.10 to 0.16 weight percent could not be cast due to excessive heat transfer, ununiform flow of slag, etc., or initial solidification factors resulting from very-high-speed casting. Therefore, thin-slab continuous casting of medium-carbon steels having a carbon

content in the peritectic range cannot be cast at present.

[0018] Consequently, an object of the present invention is to provide a mold powder which enables stable casting by reducing the likelihood of powder slag being entrapped in the mold without giving rise to surface crack when casting with a thin-slab continuous caster.

Disclosure of the Invention

[0019] As a result of a series of various investigations aimed at solving the above problems, the present inventors have discovered a mold powder capable of overcoming all of the above defects.

[0020] More specifically, the present invention relates to a mold powder as defined in the claims.

Preferred Embodiments of the Invention

[0021] As a result of a series of various investigations and research aimed at solving the above problems, the present inventors obtained the information given below.

[0022] As mentioned above, one problem has been that excessive heat transfer, non-uniformity, etc., occur as a result of very-high-speed casting, giving rise to surface crack defects and entrapment of the powder slag into the molten steel due to fluctuation of the molten surface level. With regard to the prevention of surface crack of the cast strip, this also cannot be solved by concentrating on the crystallization of the mold powder alone, which leads to the occurrence of breakouts, as explained above. However, it was found that this could be solved by adopting the following measures:

[0023] Heat transfer can be controlled by an air gap formed between the slag film and the mold. Consequently, it was found that by actively forming such an air gap, heat transfer can be reduced and mild cooling achieved, whereby the solidified shell forms uniformly and surface crack does not occur. To actively generate the air gap, the thickness of the slag film must be controlled, and it is consequently important to control the viscosity and consumption of the mold powder. In conventional high-speed casting of ordinary slabs, lubrication was considered to be important from the viewpoint of preventing breakouts, but in very-high-speed casting, the air gap is formed because the thickness of the slag film is reduced due to the high-viscosity of the mold powder, and the slag film on the solidified shell side adheres to the solidified shell and falls away. Consequently, heat transfer is controlled by setting the viscosity to a high level, and heat transfer is made uniform because the slag film is thin and therefore uniform. Furthermore, in the case of medium-carbon steel, heat transfer within the mold can be controlled together with the abovementioned air gap by controlling the crystallization temperature.

[0024] In addition, from the above viewpoint, if high viscosity is aimed for, the molten powder is less likely to be entrapped into the molten steel within the mold, making it more advantageous. Furthermore, it was found that friction between the mold and the solidified shell during very-high-speed casting is alleviated by the air gap formed between the slag film and the mold, providing further advantages against breakouts and surface crack.

[0025] Raising the viscosity of the mold powder in high-speed casting conditions used to lead to problems such as breakouts due to reduced consumption thereof. However, in very-high-speed casting at 3m or more per minute, it was found that any reduction in consumption due to high viscosity alone was small. Falling away of the slag film is considered to be influenced by the speed of movement of the solidified shell, in other words, by the casting speed. Consequently, it was confirmed that stable casting operation is achieved even if the viscosity is increased to the degree mentioned above.

[0026] Next, the mold powder according to the present invention will be explained in detail.

[0027] The weight ratio of CaO to SiO₂ in the mold powder according to the present invention is in a range of 0.5 to 1.20. It is not desirable for the weight ratio of CaO to SiO₂ to exceed 1.20 since the crystallization temperature exceeds 1200°C and becomes too high, increasing the crystal phase, thereby increasing friction between the solidified shell and the powder slag film and giving rise to breakouts, or giving rise to lateral cracking which lowers the quality of the steel. Furthermore, it is not desirable for the weight ratio of CaO to SiO₂ to be less than 0.5 because crystallization trends are significantly weakened due to reduction of the crystallization temperature of the mold powder, making the thickness of the slag film nonuniform, and also making heat transfer nonuniform. Moreover, in the mold powder for medium-carbon steel, the weight ratio of CaO to SiO₂ is in a range of 0.70 to 1.20. Here, as a mold powder for medium-carbon steel, it is not desirable for the weight ratio of CaO to SiO₂ to be less than 0.70 because the crystallization temperature falls below 1050°C, making the crystallized layer of the slag film thin and giving rise to surface crack in the cast strip because heat transfer occurs too quickly.

[0028] Carbon powder is proportioned at 0.5 to 5.0 percent by weight as a melting speed adjusting agent. It is not desirable from the standpoint of operations or quality for the proportion of carbon to be less than 0.5 percent by weight, because the slag formation reactions accelerate, and the thickness of the slag layer becomes too great, giving rise to slagbear patches. Furthermore, it is not desirable for the proportion of carbon to exceed 5 percent by weight, because the melting speed becomes too slow instead. Moreover, it is more preferable for the proportion of carbon to be within a range of 0.5 to 4.5 percent by weight.

[0029] It was found that Li_2O is an indispensable component for absorbing inclusions. That is to say, in very-high-speed casting such as thin-slab continuous casting, unless the meniscus flow speed is fast, inclusions are entrapped into the molten steel again. For that reason, it is important to increase the speed of inclusion absorption and the action of Li_2O is effective at this. The content of Li_2O is within a range of 1 to 7 percent by weight. It is not desirable for the Li_2O content to be less than 1 percent by weight, because the effects at such proportions are too weak, and it is not desirable for the content to exceed 7 percent by weight because crystallization trends are weakened instead.

[0030] Fluorine content is extremely important in controlling crystallization of the mold powder, but it is not desirable for a large amount to be used, because the crystallization temperature becomes too high, and the crystallization temperature described below exceeds 1200°C . In addition, when the F content is greater than 8.0 percent by weight, erosion of the submerged entry nozzle becomes too great and corrosion of the continuous caster machine becomes greater, thereby also increasing poisoning. Consequently, the F content is from 0.5 to 8.0 percent by weight. Furthermore, it is not desirable for the F content to be less than 0.5 percent by weight because crystallization trends are weakened and surface tension increases markedly, and it is even more preferable for the F content to be within a range of 1.0 to 6.5 percent by weight.

[0031] The crystallization temperature of the mold powder is extremely useful in controlling heat transfer within the mold. However, as mentioned above, it is not desirable for a high crystallization temperature in excess of 1200°C to be set, because friction between the solidified shell and the slag film increases and the frequency of surface crack and breakouts increases significantly. Furthermore, this is also not desirable from the aspects of deterioration in the quality of the cast strip or of stable operation because slagbear occur more easily due to the influence of variations in the molten surface during casting, and thus the crystallization temperature is from 1000 to 1200°C . On the other hand, it is not desirable for the crystallization temperature to be less than 1000°C because adhesion between the slag film and the cast strand becomes strong, leading to defects in the cast strip if the slag film is pressed in by the rollers.

[0032] Furthermore, for a mold powder for medium-carbon steel, it is preferable for the crystallization temperature to be within a range of 1050 to 1200°C , and even more preferably 1050 to 1150°C . Here, it is not desirable for the crystallization temperature to be less than 1050°C because the previously mentioned air gap formed between the slag film and the mold due to increased viscosity is reduced in size, giving rise to cracking of the cast strip. Nor is it desirable for the crystallization temperature to exceed 1200°C because friction increases and there is a risk that cracking or breakouts will occur.

[0033] The surface tension of the mold powder is extremely important in preventing the powder entrapment in the steel. In thin-slab continuous casting in particular, being very-high-speed casting in excess of 3.0 m/min, the stream speed of the molten steel at the meniscus in the mold is fast, and for that reason the formation of powdery inclusions in the molten steel due to powder slag being scraped away by the flow of molten steel is significant and causes a large defect in coil quality. Because eddy currents are generated in the vicinity of the submerged entry nozzle by this meniscus molten steel, coil quality similarly deteriorates due to the mixing in of powder slag. Consequently, the reduction of powder inclusions is important in improving coil quality. It was found that defects due to powder inclusions are significantly reduced if the surface tension is set to 250 dyne/cm or more. Consequently, it is important to adjust the surface tension of the mold powder and to maintain it at 250 dyne/cm or more at a temperature of 1300°C . However, it is preferable for the surface tension to be within a range of 250 to 500 dyne/cm because the temperature of the thermocouple for the breakout detection becomes irregular if the surface tension exceeds 500 dyne/cm, giving rise to situations in which the breakout warning alarm malfunctions.

[0034] The viscosity of the mold powder is important from the aspects of operations and quality. As mentioned above, one problem has been that cracking of the cast strip occurs in thin-slab continuous casting methods even with steel types in which cracking does not occur in conventional continuous slab casting methods. Conventional mold powders have tended to achieve low heat transfer within the mold by setting a high crystallization temperature, which instead not only caused deterioration in the quality of the cast strip but was also disadvantageous from the operations standpoint because of the occurrence of breakouts and the like. It was found that low heat transfer within the mold can be achieved, without affecting stable operations, by forming an air gap between the slag film and the mold. For this purpose, it is important to control slag film thickness, which can be achieved by adjusting viscosity.

[0035] In the case of conventional thin-slab continuous casting, the mold powders used give priority to stable operations, ensure consumption thereof, or give priority to lubrication. However, in the mold powder according to the present invention, viscosity is significantly higher than conventional products in order to control heat transfer by controlling the slag film thickness as explained above. The viscosity of the mold powder according to the present invention at 1300°C is within a range of 1.5 to 20 poise, preferably 2 to 20 poise, and even more preferably 2.5 to 20 poise. To control heat transfer within the mold, it is important to incorporate the relationship between casting speed and viscosity into the design. As a result of a series of various investigations, the present inventors have discovered that it is important to ensure that viscosity satisfies a relationship

$$6.0 \leq \eta V \leq 100.0$$

in order to establish both quality of the cast strip and stable operations in thin-slab continuous casting. Here, η is the viscosity in poise of the mold powder at 1300°C. V indicates the casting speed in meters per minute (m/min).

[0036] It is not desirable for this upper limit to be exceeded because friction increases between the solidified shell and the mold giving rise to cracking of the cast strip and breakouts instead. On the other hand, it is not desirable to fall below the lower limit because ununiform flow increases. Consequently, it is important to satisfy the above expression.

[0037] For a mold powder for a medium-carbon steel according to the present invention, it is important to ensure that viscosity satisfies a relationship

$$6.0 \leq \eta V \leq 85.0$$

in order to establish both quality of the cast strip and stable operations in thin-slab continuous casting.

[0038] Metal can be added to the mold powder according to the present invention to make it into an exothermic mold powder. In that case, it is preferable to use less than 6 percent by weight because when more than 6 percent by weight is added, slag formation time is delayed significantly.

[0039] The mold powder used can be made into granules having 90 percent by weight or more of grains having a diameter of less than 1.5 mm. It is not desirable for the content of grains with a diameter of less than 1.5 mm to be less than 90 percent by weight because the heat insulation characteristics of the mold powder decrease significantly and deckel and slagbear patches form.

[0040] The above-mentioned granulated products can be granulated by any common granulation method such as extrusion granulation, agitation granulation, flow granulation, roll granulation, spray granulation, etc. In addition, a wide range of binders can be used, from organic types such as common starch to inorganic types such as water glass.

[0041] The mold powder for thin-slab continuous casting of steel according to the present invention will now be explained further using Examples.

Example 1

[0042] Table 1 below shows mixing ratios, chemical composition, and physical property values for inventive products and comparative products. For these inventive products and comparative products, five to twenty charges each of ultra-low-carbon steels (ULC; carbon content: 30 to 60 ppm), low-carbon steels (LC; carbon content: 0.04 to 0.06 wt%), medium-carbon steels (MC; carbon content: 0.18 wt%), and high-carbon steels (HC; carbon content: 0.25 to 1 wt%) were used, and the results are given in Table 2. Thin-slab continuous casting was performed at 3.0 to 8.0 m/min and assessed.

Table 1.

Pow- der No.	Chemical composition (wt%)											viscosity 1300°C (poise)	Crystallizing temp. (°C)	Surface tension (dyn/cm)
	SiO ₂	Al ₂ O ₃	CaO	MgO	Na ₂ O	Li ₂ O	F	TiO ₂	MnO	SrO	B ₂ O ₃	Total Carbon	CaO/SiO ₂ wt. ratio	
1	41.4	7.6	27.0	2.8	7.1	3.9	5.8					4.4	0.65	260
2	39.4	7.1	31.9	4.3	6.5	1.8	5.9					3.1	0.81	280
3	38.5	5.9	36.3	4.0	4.7	1.6	5.7					3.3	0.94	300
4	40.5	5.7	39.3	0.8	2.5	6.9	2.5					2.0	0.98	425
5	35.9	5.3	42.1	0.5	5.1	2.0	6.1					3.0	1.17	360
6	40.2	6.5	33.6	3.2	5.0	5.0	3.8					2.7	0.84	340
7	37.8	5.9	34.6	3.9	4.6	3.4	5.9					3.9	0.92	360
8	37.4	6.9	40.5	0.9	2.8	2.9	5.5					3.0	1.08	450
9	41.6	6.2	35.1	0.5	6.5	3.4	5.8					0.9	0.84	325
10	43.4	7.3	32.8	0.6	7.5	2.9	5.0					0.5	0.76	285
11	34.6	6.4	40.2	0.7	6.0	2.0	5.0		1.6			3.5	1.16	360
12	40.4	6.7	34.5	0.7	6.3	2.1	5.4			0.5	0.5	2.9	0.85	390
13	40.7	6.8	34.8	0.8	3.3	6.6	2.2	1.0		0.5	0.5	2.8	1.86	350
14	45.9	8.9	34.4	0.5	0.5	4.3	0.6					4.9	0.75	480
15	51.2	9.6	28.2	0.2	0.2	5.9	0.5					4.2	0.55	490
Comparison														
1	33.7	4.6	31.2	5.2	10.5	3.4	8.4					3.0	0.93	220
2	31.9	3.2	39.1	1.6	9.1	2.7	9.2					3.2	1.23	200
Present invention														

[0043] In Table 1, synthetic calcium silicate with a CaO/SiO₂ weight ratio equal to 1.10 was used as the main raw material for Inventive Products 1, 2, 3, 4, 6, 7, 9, 10, and 12 to 15 and Comparative Product 1, and synthetic calcium silicate with a CaO/SiO₂ weight ratio equal to 1.35 was used for the rest. Furthermore, glass powder, diatomaceous earth, and spodumene were used as the SiO₂ materials in the mold powder in all cases in Table 1. In addition, Na₂CO₃, Li₂CO₃, MnCO₃, SrCO₃, NaF, Na₃AlF₆, CaF₂, Al₂O₃, MgO, LiF, TiO₂, ZrO₂, and B₂O₃ used as flux materials were adjusted and proportioned to make the chemical compositions given in Table 1 and mixed using a mixer. Moreover, carbon black and coke powder were used for the carbon source in all of the mold powders, being added to make the chemical compositions given in Table 1. Furthermore, 2.8 percent by weight of metal Si was added to Inventive Product 9 and 4.4 percent by weight of metal Ca-Si alloy was added to Inventive Product 10, and mixed similarly. In addition, Inventive Product 7 was a granulated product in which 20 to 30 percent by weight of a solvent composed of 90 percent by weight of water and 10 percent by weight of sodium silicate was added to the mixture to form a slurry which was spray granulated and dried. In Inventive Product 8, 10 to 16 percent by weight of a solvent composed of 95 percent by weight of water and 5 percent by weight of starch paste was added to the mixture agitation granulated and dried.

Table 2.

	Powder No.	Kind of steel	Casting rate	Breakouts	Pinhole	crack	Powdery inclusions
Present invention	1	H.C	3.5	△	○	△	○
	2	LC	5.5	○	○	○	○
	3	LC	7.0	○	○	○	○
	4	ULC	8.0	○	△	○	△
	5	M.C	6.0	○	○	○	△
	6	ULC&LC	5.0	○	○	○	○
	7	LC	7.0	○	○	○	○
	8	M.C	5.0	○	○	△	○
	9	LC	6.0	○	○	○	○
	10	ULC&HC	3.0	○	○	○	○
	11	M.C	6.0	○	△	○	○
	12	LC	4.0	○	△	○	○
	13	ULC	5.0	△	○	○	○
	14	LC	5.0	○	○	○	○
	15	LC	5.5	△	○	○	○
Comparison							
	1	LC&ULC	6.0	×	×	×	×
	2	M.C	4.0	×	△	△	×

[0044] In the results shown in Table 2, for breakouts ○ indicates no occurrence, △ indicates only one occurrence, and × indicates two or more occurrences. For powder inclusions, ○ indicates that the proportion defective was 0%, △ indicates up to 1%, and × indicates greater than 1% or more. For pin holes and cracking, ○ indicates no occurrence, △ indicates one per m², and × indicates two or more occurrences per m².

Example 2

[0045] Table 3 below shows mixing ratios, chemical composition, and physical property values for inventive products and comparative products. For these inventive products and comparative products, four to twenty charges each of sub-peritectic medium-carbon steels (carbon content: 0.08 to 0.15 wt%) were used, and the results are given in Table 4. Thin-slab continuous casting was performed at 3.0 to 8.0 m/min and assessed.

Table 3.

Pow- der No.	Chemical composition (wt%)										viscosity 1300°C (poise)	Crystallizing temp. (°C)	Surface tension (dyn/cm)				
	SiO ₂	Al ₂ O ₃	CaO	MgO	Na ₂ O	Li ₂ O	F	TiO ₂	MnO	ZrO				Total Carbon	CaO/SiO ₂ wt ratio		
Present invention	16	38.1	5.4	39.0	1.0	4.9	1.0	7.5				3.1	1.03	2.5	1110	340	
	17	36.8	6.1	40.6	0.8	4.7	1.1	7.0				2.9	1.10	2.0	1150	345	
	18	36.9	6.7	40.9	0.8	4.7	2.4	4.5				3.1	1.11	2.7	1130	390	
	19	35.2	7.0	41.7	0.7	4.8	1.9	4.8				3.9	1.18	2.5	1185	400	
	20	37.4	6.8	41.7	0.8	4.8	1.9	2.8				3.8	1.12	3.7	1190	450	
	21	37.4	4.2	39.8	0.8	6.2	3.4	4.8				3.4	1.06	1.7	1150	370	
	22	37.6	6.7	40.5	0.8	4.4	2.0	5.9				2.1	1.08	2.8	1140	375	
	23	36.5	6.8	41.5	2.0	4.4	2.1	4.7				2.0	1.14	2.5	1170	390	
	24	40.3	6.7	40.8	1.9	4.3	2.4	2.8				0.8	1.01	4.2	1130	410	
	25	38.1	6.4	44.6	1.8	4.5	1.8	1.8				0.9	1.17	3.8	1190	380	
Comparison	26	36.3	5.1	41.9	1.7	4.3	1.7	5.1	0.9	0.9		2.1	1.15	2.0	1180	320	
	27	38.0	5.0	40.9	0.7	4.2	1.7	5.0		2.0	0.8	2.4	1.08	2.8	1170	345	
	28	47.3	8.7	33.6	0.8	0.5	4.2	0.5				4.4	0.71	10.0	1050	450	
	29	46.8	9.9	35.6	0.2	0.1	4.7	0.5				2.2	0.76	15.0	1060	460	
	30	41.1	9.8	40.2	0.8	0.6	3.6	1.0				4.2	0.98	9.0	1030	490	
	3	40.8	4.8	38.4	1.6	4.0	2.8	5.6				3.0	0.94	2.8	970	300	
	4	36.1	5.2	44.4	1.7	4.4	1.2	4.5				3.5	1.23	2.1	1215	260	
	5	33.2	3.6	40.8	0.6	8.0	1.6	9.2				3.0	1.23	0.6	1190	240	

[0046] In Table 3, synthetic calcium silicate with a CaO/SiO₂ weight ratio equal to 1.35 was used as the main raw material for Inventive Products 19, 20, 24, and 25, and synthetic calcium silicate with a CaO/SiO₂ weight ratio equal to 1.10 was used for the rest. Furthermore, glass powder, diatomaceous earth, and spodumene were used as the SiO₂ materials in the mold powder in all cases in Table 3.

[0047] In addition, Na₂CO₃, Li₂CO₃, MnCO₃, SrCO₃, NaF, Na₃AlF₆, CaF₂, Al₂O₃, MgO, LiF, TiO₂, ZrO₂, and B₂O₃ used as flux materials were adjusted and proportioned to make the chemical compositions given in Table 3 and mixed using a mixer. Moreover, carbon black and coke powder were used for the carbon source in all of the mold powders, being added to make the chemical compositions given in Table 3. Furthermore, 2.5 percent by weight of metal Si was added to Inventive Product 24 and 4.4 percent by weight of metal Ca-Si alloy was added to Inventive Product 25, and mixed similarly.

[0048] In addition, Inventive Product 22 was a granulated product in which 20 to 30 percent by weight of a solvent composed of 90 percent by weight of water and 10 percent by weight of sodium silicate was added to the mixture to form a slurry which was spray granulated and dried. In Inventive Product 24, 10 to 16 percent by weight of a solvent composed of 95 percent by weight of water and 5 percent by weight of starch paste was added to the mixture agitation granulated and dried.

Table 4.

	Powder No.	Casting rate	Breakouts	Pinhole	crack	Powdery inclusions
Present invention	16	5.0	○	○	△	○
	17	7.5	○	○	○	○
	18	4.5	○	○	○	○
	19	4.0	○	△	○	○
	20	3.5	○	○	○	○
	21	8.0	○	○	○	△
	22	5.0	○	○	○	○
	23	4.0	○	○	○	○
	24	3.0	○	○	△	○
	25	3.5	○	○	○	○
	26	6.0	○	△	○	○
	27	5.0	○	△	○	○
	28	5.5	○	△	○	○
	29	5.0	○	○	△	○
	30	6.0	○	○	○	○
Comparison						
	3	5.0	×	×	×	×
	4	6.0	×	×	△	×
	5	4.5	×	×	×	×

[0049] In the results shown in Table 4, for breakouts ○ indicates no occurrence, △ indicates only one occurrence, and × indicates two or more occurrences. For powder inclusions, ○ indicates that the proportion defective was 0%, △ indicates up to 1%, and × indicates greater than 1% or more. For pin holes and cracking, ○ indicates no occurrence, △ indicates one per m², and × indicates two or more occurrences per m².

Possibility of Use in Industry

[0050] The present invention exhibits the effect that a mold powder can be provided which enables stable casting by reducing the likelihood of powder entrapment into the mold without giving rise to surface crack in the cast strip when casting with a thin-slab continuous caster.

Claims

1. A mold powder for thin-slab continuous casting of steel, containing one or two or more species selected from the group consisting of oxides, carbonates, or fluorides of alkali metals, alkaline earth metals, or other metals besides calcium silicate in such an amount that the total amount, calculated on the basis of the oxides Li_2O , MgO , Na_2O and Al_2O_3 is from 11.6 to 21.4 weight percent with respect to the total weight of the mold powder, wherein the Li_2O content is within the range of 1 to 7 weight percent, the MgO content is within the range of 0.2 to 4.3 weight percent, the Na_2O content is within the range of 0.1 to 7.5 weight percent, and the Al_2O_3 content is within the range of 5.0 to 9.9 weight percent; and 0.5 to 5 percent by weight of carbon powder; and optionally 6 percent by weight or less of metal powder or alloy powder; wherein the fluorine content is within the range of 0.5 to 8.0 percent by weight; and as main component calcium silicate with a weight ratio of CaO to SiO_2 within the range of 0.50 to 1.2, being the balance of the mold powder, wherein the crystallization temperature is within the range of 1000 to 1200°C; the surface tension at 1300°C is 250 dyne/cm or more; and the viscosity at 1300°C is within the range of 1.5 to 20 poise.
2. A mold powder for thin-slab continuous casting of medium-carbon steel, containing one or two or more species selected from the group consisting of oxides, carbonates, or fluorides of alkali metals, alkaline earth metals, or other metals besides calcium silicate in such an amount that the total amount, calculated on the basis of the oxides Li_2O , MgO , Na_2O and Al_2O_3 is from 11.6 to 21.4 weight percent with respect to the total weight of the mold powder, wherein the Li_2O content is within the range of 1 to 7 weight percent, the MgO content is within the range of 0.2 to 4.3 weight percent, the Na_2O content is within the range of 0.1 to 7.5 weight percent, and the Al_2O_3 content is within the range of 5.0 to 9.9 weight percent; and 0.5 to 5 percent by weight of carbon powder; and optionally 6 percent by weight or less of metal powder or alloy powder; wherein the fluorine content is within the range of 0.5 to 8.0 percent by weight; and as main component calcium silicate with a weight ratio of CaO to SiO_2 within the range of 0.70 to 1.2, being the balance of the mold powder; the crystallization temperature is within the range of 1050 to 1200°C; the surface tension at 1300°C is 250 dyne/cm or more; and the viscosity at 1300°C is within the range of 1.5 to 20 poise.
3. A process for thin-slab continuous casting of steel, wherein the mold powder according to claim 1 is used, in which the casting speed is set to 3 m/min or greater, and wherein the relationship between viscosity (poise) at 1300°C and casting speed V (m/min) satisfies the range represented by the expression:

$$6.0 \leq \eta V \leq 100.0.$$

4. A process for thin-slab continuous casting of medium-carbon steel, wherein the mold powder according to claim 2 is used, in which the casting speed is set to 3m/min or greater, and wherein the relationship between viscosity (poise) at 1300°C and casting speed V (m/min) satisfies the range represented by the expression:

$$6.0 \leq \eta V \leq 85.0.$$

5. The method according to claim 4, wherein the carbon content in the medium-carbon steel is within the range of 0.08

to 0.18 percent by weight.

Patentansprüche

1. Abdeckpulver für das Dünnbrammen-Stranggießen von Stahl, das enthält:

eine oder zwei oder mehr Spezies, ausgewählt aus der Gruppe, bestehend aus Oxiden, Carbonaten oder Fluoriden von Alkalimetallen, Erdalkalimetallen oder anderen Metallen, mit Ausnahme von Kalziumsilikat, in einer solchen Menge, dass die Gesamtmenge, berechnet auf Basis der Oxide Li_2O , MgO , Na_2O und Al_2O_3 11,6 bis 21,4 Gew.-% in Bezug auf das Gesamtgewicht des Abdeckpulvers ist, wobei der Li_2O -Gehalt im Bereich von 1 bis 7 Gew.-% liegt, der MgO -Gehalt im Bereich von 0,2 bis 4,3 Gew.-% liegt, der Na_2O -Gehalt im Bereich von 0,1 bis 7,5 Gew.-% liegt und der Al_2O_3 -Gehalt im Bereich von 5,0 bis 9,9 Gew.-% liegt; und 0,5 bis 5 Gew.-% Kohlenstoffpulver; und ggf. 6 Gew.-% oder weniger Metallpulver oder Legierungspulver; wobei der Fluorgehalt im Bereich von 0,5 bis 8,0 Gew.-% liegt; und als Hauptkomponente Kalziumsilicat mit einem Gewichtsverhältnis von CaO zu SiO_2 im Bereich von 0,50 bis 1,2, welches den Ausgleich des Abdeckpulvers bildet, wobei die Kristallisationstemperatur im Bereich von 1000 bis 1200°C liegt; die Oberflächenspannung bei 1300°C 250 Dyne/cm oder mehr ist; und die Viskosität bei 1300°C im Bereich von 1,5 bis 20 Poise liegt.

2. Abdeckpulver für das Dünnbrammen-Stranggießen von Stahl mit mittlerem Kohlenstoffgehalt, das enthält:

eine oder zwei oder mehr Spezies, ausgewählt aus der Gruppe, bestehend aus Oxiden, Carbonaten oder Fluoriden von Alkalimetallen, Erdalkalimetallen oder anderen Metallen, mit Ausnahme von Kalziumsilikat, in einer solchen Menge, dass die Gesamtmenge, berechnet auf Basis der Oxide Li_2O , MgO , Na_2O und Al_2O_3 11,6 bis 21,4 Gew.-% in Bezug auf das Gesamtgewicht des Abdeckpulvers ist, wobei der Li_2O -Gehalt im Bereich von 1 bis 7 Gew.-% liegt, der MgO -Gehalt im Bereich von 0,2 bis 4,3 Gew.-% liegt, der Na_2O -Gehalt im Bereich von 0,1 bis 7,5 Gew.-% liegt und der Al_2O_3 -Gehalt im Bereich von 5,0 bis 9,9 Gew.-% liegt; und 0,5 bis 5 Gew.-% Kohlenstoffpulver; und ggf. 6 Gew.-% oder weniger Metallpulver oder Legierungspulver; wobei der Fluorgehalt im Bereich von 0,5 bis 8,0 Gew.-% liegt; und als Hauptkomponente Kalziumsilicat mit einem Gewichtsverhältnis von CaO zu SiO_2 im Bereich von 0,70 bis 1,2, welches den Ausgleich des Abdeckpulvers bildet, wobei die Kristallisationstemperatur im Bereich von 1050 bis 1200°C liegt; die Oberflächenspannung bei 1300°C 250 Dyne/cm oder mehr ist; und die Viskosität bei 1300°C im Bereich von 1,5 bis 20 Poise liegt.

3. Verfahren zum Dünnbrammen-Stranggießen von Stahl, bei dem das Abdeckpulver gemäß Anspruch 1 verwendet wird, bei dem die Gießgeschwindigkeit auf 3 m/min oder größer eingestellt ist und bei dem die Beziehung zwischen der Viskosität (Poise) bei 1300°C und der Gießgeschwindigkeit V (m/min) den Bereich erfüllt, der wiedergegeben ist durch den Ausdruck:

$$6,0 \leq \eta V \leq 100,0$$

4. Verfahren zum Dünnbrammen-Stranggießen von Stahl, bei dem das Abdeckpulver gemäß Anspruch 2 verwendet wird, bei dem die Gießgeschwindigkeit auf 3 m/min oder größer eingestellt ist und bei dem die Beziehung zwischen der Viskosität (Poise) bei 1300°C und der Gießgeschwindigkeit V (m/min) den Bereich erfüllt, der wiedergegeben ist durch den Ausdruck:

$$6,0 \leq \eta V \leq 85,0$$

5. Verfahren gemäß Anspruch 4, bei dem der Kohlenstoffgehalt in dem Stahl mit mittlerem Kohlenstoffgehalt im Bereich

von 0,08 bis 0,18 Gew.-% liegt.

Revendications

1. Poudre de couverture pour la coulée en continu de brames minces en acier, contenant une ou deux espèces ou plus sélectionnées dans le groupe constitué d'oxydes, de carbonates, ou de fluorures de métaux alcalins, de métaux alcalino-terreux ou d'autres métaux hormis le silicate de calcium en une quantité telle que la quantité totale, calculée sur la base des oxydes Li_2O , MgO , Na_2O et Al_2O_3 est de 11,6 à 21,4 pourcent en poids par rapport au poids total de la poudre de couverture, dans laquelle la teneur en Li_2O est de l'ordre de 1 à 7 pourcent en poids, le teneur en MgO est de l'ordre de 0,2 à 4,3 pourcent en poids, la teneur en Na_2O est de l'ordre de 0,1 à 7,5 pourcent en poids, et la teneur en Al_2O_3 est de l'ordre de 5,0 à 9,9 pourcent en poids ; et 0,5 à 5 pourcent en poids de poudre de carbone ; et optionnellement 6 pourcent en poids ou moins de poudre métallique ou de poudre d'alliage ; dans laquelle la teneur en fluor est de l'ordre de 0,5 à 8,0 pourcent en poids ; et comme composant principal, le silicate de calcium avec un rapport pondéral du CaO au SiO_2 de l'ordre de 0,50 à 1,2, constituant le reste de la poudre de couverture, dans laquelle la température de cristallisation est de l'ordre de 1 000 à 1 200°C ; la tension superficielle à 1 300°C est de 250 dyne/cm ou plus ; et la viscosité à 1 300°C est de l'ordre de 1,5 à 20 poise.
2. Poudre de couverture pour la coulée en continu de brames minces en acier à carbone moyen, contenant une ou deux espèces ou plus sélectionnées dans le groupe constitué d'oxydes, de carbonates, ou de fluorures de métaux alcalins, de métaux alcalino-terreux, ou d'autres métaux hormis le silicate de calcium en une quantité telle que la quantité totale, calculée sur la base des oxydes Li_2O , MgO , Na_2O et Al_2O_3 est de 11,6 à 21,4 pourcent en poids par rapport au poids total de la poudre de couverture, dans laquelle la teneur en Li_2O est de l'ordre de 1 à 7 pourcent en poids, le teneur en MgO est de l'ordre de 0,2 à 4,3 pourcent en poids, la teneur en Na_2O est de l'ordre de 0,1 à 7,5 pourcent en poids, et la teneur en Al_2O_3 est de l'ordre de 5,0 à 9,9 pourcent en poids ; et 0,5 à 5 pourcent en poids de poudre de carbone ; et optionnellement 6 pourcent en poids ou moins de poudre métallique ou de poudre d'alliage ; dans laquelle la teneur en fluor est de l'ordre de 0,5 à 8,0 pourcent en poids ; et comme composant principal, le silicate de calcium avec un rapport pondéral du CaO au SiO_2 de l'ordre de 0,70 à 1,2, constituant le reste de la poudre de couverture ; la température de cristallisation est de l'ordre de 1 050 à 1 200°C ; la tension superficielle à 1 300°C est de 250 dyne/cm ou plus ; et la viscosité à 1 300°C est de l'ordre de 1,5 à 20 poise.
3. Procédé pour la coulée en continu de brames minces en acier, dans lequel la poudre de couverture selon la revendication 1 est utilisée, dans lequel la vitesse de coulée est réglée à 3 m/min ou plus, et dans lequel la relation entre la viscosité (poise) à 1 300°C et la vitesse de coulée V (m/min) satisfait la plage représentée par l'expression :

$$6,0 \leq \eta V \leq 100,0.$$

4. Procédé pour la coulée en continu de brames minces en acier à carbone moyen, dans lequel la poudre de couverture selon la revendication 2 est utilisée, dans lequel la vitesse de coulée est réglée à 3 m/min ou plus, et dans lequel la relation entre la viscosité (poise) à 1 300°C et la vitesse de coulée V (m/min) satisfait la plage représentée par l'expression :

$$6,0 \leq \eta V \leq 85,0.$$

5. Méthode selon la revendication 4, dans laquelle la teneur en carbone dans l'acier à carbone moyen est de l'ordre de 0,08 à 0,18 pourcent en poids.